

GUANTE GUANTES DE PU JUBA - 4410RF POWER CUT

Dyneema® mixed with fibreglass glove with PU coating on palm and fingers. Reinforcement between index and thumb







NORMATIVE













CHARACTERISTICS

- Dyneema® fibre is a high technology product and guarantees a total and durable protection from cuts and abrasions.
- Dyneema® fibre is washable.
- Dyneema® label guaranteeing quality.
- Its flexibility, lightness and fresh touch offer great comfort and breathability for the user.
- Ergonomic design perfectly fits the hand, thus minimizing hand fatigue and increasing tactility.
- Excellent mechanical performance.
- Greater durability and strength due to the combination of fibres and palm PU coating.
- Handling and grip on any surface, oiled or dry.

WORKING GLOVES SUITABLE FOR:

- Glass industry.
- Automotive sector.
- · Machine operations.
- · Metal fabrication.
- · Ceramics.
- Paper and pulp industry.
- Applications requiring ultimate cut protection.
- Those works requiring extra reinforcement between index and thumb.

Distributed by:





- According to the standard EN 1149-5:2008 for textile materials, the fabric analysed can be classified as antistatic.
- Water-based PU reinforcement between index and thumb.

| MORE INFO | MORE INFO | | | | | | |
|--------------|--------------|-----------|--|--------------------------------------|-----------------------------------|--|--|
| Materials | Colour | Thickness | Length | Sizes | Packaging | | |
| Polyurethane | Grey / White | Gauge 10 | S - 23 cm M - 24 cm L - 25 cm XL - 26 cm XXL - 27 cm | 7/S 8/M 9/L 10/XL 11/XXL | 10 pairs/package 120 pairs/box | | |


NORMATIVAS



EN388:2016 Protective gloves against mechanical risks.

The EN388: 2003 standard is renamed EN388: 2016, the year of its revision. The reason for the modification is given by the discrepancies in the results between laboratories in the knife cut test, COUP TEST. Materials with high levels of cut produce a dulling effect on the circular blades, which undermines the result.

The new regulation was published in November 2016 and the previous one is from the year 2003. During these 13 years, there has been a great innovation in the materials for the manufacture of cutting gloves, they have forced to introduce changes in the tests to be able to measure with more rigorous levels of protection. If you want to know more about the main changes in these regulations, you can consult it through our website www.jubappe.es



- A Abrasion resistance (X, 0, 1, 2, 3, 4)
- B Blade Cut Resistance (X, 0, 1, 2, 3, 4, 5) C Tear resistance (X, 0, 1, 2, 3, 4) D Puncture resistance (X, 0, 1, 2, 3, 4)

- E Cutting by sharp objects ISO 13997 (A, B, C, D, E, F)
- F Impact test complies / does not comply (It is optional. If it complies, put

| En388:2016 performance levels | 1 | 2 | 3 | 4 | 5 |
|-----------------------------------|-----|-----|------|------|----|
| 6.1 abrasion resistance (cycles) | 100 | 500 | 2000 | 8000 | - |
| 6.2 blade cut resistance (index) | 1,2 | 2,5 | 5 | 10 | 20 |
| 6.4 tear resistance (newtons) | 10 | 25 | 50 | 75 | - |
| 6.5 puncture resistance (newtons) | 20 | 60 | 100 | 150 | - |

| Eniso13997:1999 performance levels | Α | В | С | D | E | F | |
|------------------------------------|---|---|----|----|----|----|--|
| 6.3 tdm: cut resistance (newtons) | 2 | 5 | 10 | 15 | 22 | 30 | |

Distributed by:

