

GUANTE JUBA - 4438 POWER CUT

Dyneema® mixed with fibreglass sleeve



NORMATIVE



CHARACTERISTICS

- The Dyneema® fiber is known worldwide for its high strength and is used for the manufacture of gloves with cutting protection.
- Washable at 40°C.
- Very light and flexible.
- Does not leave lint.
- Sensation of freshness for its great breathability.
- To wear on top of clothing as it is unicapa construction.
- It should be worn with an appropriate glove on top.
- Suitable for food use.

WORKING GLOVES SUITABLE FOR:

- Food industry.
- Glass industry.
- Sheet metal handling.
- Automotive.
- Aeronautics.
- Appliance industry.
- Machining parts.

Distributed by:



MORE INFO

Colour	Thickness	Length	Packaging
White	Gauge 10	U - 45 cm	12 unit/package 144 unidades/caja

NORMATIVAS


EN388:2016



EN388:2016 Protective gloves against mechanical risks.

The EN388: 2003 standard is renamed EN388: 2016, the year of its revision. The reason for the modification is given by the discrepancies in the results between laboratories in the knife cut test, COUP TEST. Materials with high levels of cut produce a dulling effect on the circular blades, which undermines the result.

The new regulation was published in November 2016 and the previous one is from the year 2003. During these 13 years, there has been a great innovation in the materials for the manufacture of cutting gloves, they have forced to introduce changes in the tests to be able to measure with more rigorous levels of protection. If you want to know more about the main changes in these regulations, you can consult it through our website www.jubappe.es



- A - Abrasion resistance (X, 0, 1, 2, 3, 4)
- B - Blade Cut Resistance (X, 0, 1, 2, 3, 4, 5)
- C - Tear resistance (X, 0, 1, 2, 3, 4)
- D - Puncture resistance (X, 0, 1, 2, 3, 4)
- E - Cutting by sharp objects ISO 13997 (A, B, C, D, E, F)
- F - Impact test complies / does not comply (It is optional. If it complies, put P)

En388:2016 performance levels	1	2	3	4	5
6.1 abrasion resistance (cycles)	100	500	2000	8000	-
6.2 blade cut resistance (index)	1,2	2,5	5	10	20
6.4 tear resistance (newtons)	10	25	50	75	-
6.5 puncture resistance (newtons)	20	60	100	150	-

Eniso13997:1999 performance levels	A	B	C	D	E	F
6.3 tdm: cut resistance (newtons)	2	5	10	15	22	30

Distributed by:

