

Stone - jacket

description

• mobile phone pocket with E-CARE • loop for headset • wide breast and bottom pockets • pen pocket • wide internal pockets • arm ergonomic design • YKK® zip

maintenance

maximum wash temperature: 60°C - do not bleach - dry cleaning allowed - drying in tumble dryer not allowed - medium iron temperature: 110°C



item

V060-0-00 khaki/black
V060-0-01 grey/black
V060-0-02 navy/black
V060-0-03 brown/black
V060-0-04 anthracite/black
V060-0-05 black/black

Standards

EN ISO 13688:2013



Sizes

44 – 64

SAFETY TECHNICAL SPECIFICATIONS

Test method	description	Cofra result	minimum requirement / range
Background fabric EN ISO 1833-1977, SECTION 10	Composition: Cotton/polyester	60 / 40 %	
	Weave: twill 3/1	Warp : 8 [yarn/cm] Weft : 6 [yarn/cm]	
EN ISO 12127:1996	Weight per unit area	245 g/sqm	
EN ISO 105-C06 E2S: 1994	Colour fastness to washes (60°C)	Colour change: 4 Staining: 4	1 - 5 1 - 5
EN ISO 105 D01:1993	Colour fastness to dry cleaning	Colour change: 4 – 5	1 - 5
ISO 5077:1994, ISO 6330: 1994	Dimensional change to washes (60°C)	warp: - 0.8 % weft: - 1.0 %	Max ± 3 % Max ± 3 %
ISO 105X12: 2001	Colour fastness to rubbing	dry: 5 weft: 4 - 5	1 - 5 1 - 5
EN ISO 105 B02: 1993, METODO 3	Colour fastness to light	4	1 - 5
ISO 105-N01:1993	Colour fastness to bleaching	Colour change: 4	1 – 5
EN ISO 13934-2: 1999	Tensile strength	warp: 1351 N weft: 830 N	400 N 400 N
EN340/03 paragraph 4.2 (EN 1413)	The PH's determination from the watery extract	PH 6.92	3,5<PH≤9,5
EN340/03 paragraph 4.2 (prEN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
E-care	Composition: PES/CO/MTF	65/33/2%	
	Weight per unit area	215 g/sqm	
	Yarns/cm	warp: 34 weft: 22	
DIN 53857/1	Tensile strength	warp: 100 daN weft: 65 daN	
DIN 53892 (3 cicli a 95°C)	Dimensional change to washes	1.5%	
DIN 54004 (ISO 105B02)	Colour fastness to light	5	1 - 5

TECHNICAL SHEET

DIN 54020 (ISO 105E04)	Colour fastness to perspiration	Colour change: 4	1 - 5
		staining: 3-4	1 - 5
DIN 54021 (ISO 105X12)	Colour fastness to rubbing	dry: 4	1 - 5
		wet: 2-3	1 - 5
DIN 54024 (ISO 105N01)	Colour fastness to bleaching	4	1 - 5
MIL-Standard 285	Attenuation measurements for enclosures, electromagnetic shielding, for electronic test purposes	Reduction of 99,5% of the electromagnetic waves to the frequency of 200 MHz	
		Reduction of 99% of the electromagnetic waves to the frequency of 2000 MHz	

Distributed by:

